

PRODUCT DATA SHEET

BAGGES CGF-1

Description : Filament FORTAGLAS™ “E” Glass fabric, a low level of applied weavelock

Properties			
Weave	Plain		
Finish	Finish Organic Weavelock (2%)		
Weight (g/m ²)	204		
Thickness (mm)	0,20		
Cloth construction	Ends / dm - 170 Picks / dm - 120		
Tensile strength	Warp (N/50 mm) - 1300 Weft (N/50 mm) - 1800		
Flammability	<table border="1" style="width: 100%;"> <tr> <td style="width: 30%;"> BS476 Part 7: 1987 (indicative) BS476 Part 6: 1989 (indicative) </td> <td> Surface spread of flame - class 1 pass (highest level of performance that can be achieved against this standard) Fire propagation Index = 1.78 (sub-indices i1 = 1.60; i2 = 0.17; i3 = 0.01) Indicatively meets the requirements of Class 0 of the UK building regulation 1991 (2000 edition) Approved document B appendix A paragraph 12 </td> </tr> </table>	BS476 Part 7: 1987 (indicative) BS476 Part 6: 1989 (indicative)	Surface spread of flame - class 1 pass (highest level of performance that can be achieved against this standard) Fire propagation Index = 1.78 (sub-indices i1 = 1.60; i2 = 0.17; i3 = 0.01) Indicatively meets the requirements of Class 0 of the UK building regulation 1991 (2000 edition) Approved document B appendix A paragraph 12
BS476 Part 7: 1987 (indicative) BS476 Part 6: 1989 (indicative)	Surface spread of flame - class 1 pass (highest level of performance that can be achieved against this standard) Fire propagation Index = 1.78 (sub-indices i1 = 1.60; i2 = 0.17; i3 = 0.01) Indicatively meets the requirements of Class 0 of the UK building regulation 1991 (2000 edition) Approved document B appendix A paragraph 12		
Roll length (metres)	50 upward		
Roll width (cm)	91.5 to 183. On stock: 100 cm		
Availability	Ex stock dependent upon width		

NB: Unless otherwise stated, all values quoted are nominal measurements The information contained in this data sheet is believed to be true at the time of printing. Any statements contained or inferred to within are an expression of opinion and presented without guarantee. It is up to the user to determine suitability of use, or potential patent infringement for specific applications.