

PRODUCT DATA SHEET

BAGGES BMF

Properties											
Description	Mineral fibres and high temperature bonds, added a small amount of starch.										
Classification Temperature	1000°C										
Colour	Green										
Density	240 Kg/m ³										
Organic Content	5%										
Shrinkage (24 hrs at classification temp)	3										
Flexural Strength	1,7 MPa										
Thermal Conductivity	<table style="width: 100%; border: none;"> <tr> <td style="width: 60%;">@Mean Temp 200 deg C</td> <td style="text-align: right;">0,05</td> </tr> <tr> <td>@Mean Temp 400 deg C</td> <td style="text-align: right;">0,07</td> </tr> <tr> <td>@Mean Temp 600 deg C</td> <td style="text-align: right;">0,09</td> </tr> <tr> <td>@Mean Temp 800 deg C</td> <td style="text-align: right;">-</td> </tr> <tr> <td>@Mean Temp 1000 deg C</td> <td style="text-align: right;">-</td> </tr> </table>	@Mean Temp 200 deg C	0,05	@Mean Temp 400 deg C	0,07	@Mean Temp 600 deg C	0,09	@Mean Temp 800 deg C	-	@Mean Temp 1000 deg C	-
@Mean Temp 200 deg C	0,05										
@Mean Temp 400 deg C	0,07										
@Mean Temp 600 deg C	0,09										
@Mean Temp 800 deg C	-										
@Mean Temp 1000 deg C	-										
Classification EC 97/69	Exonerated										
Fire Tests	In accordance with BS 476: Part 11: 1982										
Availability	Ex stock subject to being unsold										

NB: Unless otherwise stated, all values quoted are nominal measurements. The information contained in this data sheet is believed to be true at the time of printing. Any statements contained or inferred to within are an expression of opinion and presented without guarantee. It is up to the user to determine suitability of use, or potential patent infringement for specific applications.

rev: 08/2021