

PRODUCT DATA SHEET

BAGGES WGF

Properties				
	WGF 1.5mm		WGF 3.0mm	
Description	Textured FORTAGLAS™ Webbing		Textured FORTAGLAS™ Webbing	
Weave	Half - matt wef		2 x 2 twill	
Finish	Loomstate		Loomstate	
Standard widths (mm) (mm) (mm) (mm)	<u>Available ex-stock</u> 25 nominal 25 nominal		<u>Available ex-stock</u> 40 nominal 50 nominal 65 nominal 100 nominal	
Other widths	Made to order on request		Made to order on request	
Standar manufacturing quantity (metres)	1000		1000	
Weight/30 metre coil mm/kg mm/kg mm/kg mm/kg mm/kg mm/kg	<u>Width</u> 25	<u>Weight</u> 0,70	<u>Width</u> 40 50 65 100	<u>Weight</u> 1,63 2,09 3,18 4,06
Webbing construction Ends / dm Picks / dm	38 nominal 15 double picks		86 19 double picks	
Thermal conductivity (W/mK)	1.0 nominal for "E" glass		1.0 nominal for "E" glass	
Classification temperature	+550°C		+550°C	
Sark iii release tested in accordance with ASTM F607				

NB: Unless otherwise stated, all values quoted are nominal measurements The information contained in this data sheet is believed to be true at the time of printing. Any statements contained or inferred to within are an expression of opinion and presented without guarantee. It is up to the user to determine suitability of use, or potential patent infringement for specific applications.