

PRODUCT DATA SHEET

BAGGES CSF-15

Properties																																									
Base Fabric	<table border="1" style="width: 100%; border-collapse: collapse;"> <thead> <tr style="background-color: #cccccc;"> <th colspan="4" style="text-align: left; padding: 5px;">Description</th> <th style="text-align: left; padding: 5px;">Tolerance</th> <th style="text-align: left; padding: 5px;">Test Methods</th> </tr> </thead> <tbody> <tr> <td style="padding: 5px;">Yarn</td> <td style="padding: 5px;">Warp Weft</td> <td style="padding: 5px;">ET9 ET9</td> <td style="padding: 5px;">620 tex + V4A 620 tex + V4A</td> <td style="padding: 5px;">+/- 5% +/- 5%</td> <td style="padding: 5px;">DIN 53830-3</td> </tr> <tr> <td style="padding: 5px;">Thread Count</td> <td style="padding: 5px;">Warp Weft</td> <td style="padding: 5px;">12,0 6,0</td> <td style="padding: 5px;">1/cm 1/cm</td> <td style="padding: 5px;">+/- 5% +/- 5%</td> <td style="padding: 5px;">DIN EN 1049-2</td> </tr> <tr> <td style="padding: 5px;">Weight</td> <td style="padding: 5px;">1.200</td> <td style="padding: 5px;">g/cm2</td> <td></td> <td style="padding: 5px;">+/-5%</td> <td style="padding: 5px;">DIN EN 12127</td> </tr> <tr> <td style="padding: 5px;">Weave</td> <td></td> <td style="padding: 5px;">Panama</td> <td></td> <td></td> <td style="padding: 5px;">ISO 9354</td> </tr> </tbody> </table>					Description				Tolerance	Test Methods	Yarn	Warp Weft	ET9 ET9	620 tex + V4A 620 tex + V4A	+/- 5% +/- 5%	DIN 53830-3	Thread Count	Warp Weft	12,0 6,0	1/cm 1/cm	+/- 5% +/- 5%	DIN EN 1049-2	Weight	1.200	g/cm2		+/-5%	DIN EN 12127	Weave		Panama			ISO 9354						
Description				Tolerance	Test Methods																																				
Yarn	Warp Weft	ET9 ET9	620 tex + V4A 620 tex + V4A	+/- 5% +/- 5%	DIN 53830-3																																				
Thread Count	Warp Weft	12,0 6,0	1/cm 1/cm	+/- 5% +/- 5%	DIN EN 1049-2																																				
Weight	1.200	g/cm2		+/-5%	DIN EN 12127																																				
Weave		Panama			ISO 9354																																				
Coated Fabric	<table border="1" style="width: 100%; border-collapse: collapse;"> <thead> <tr style="background-color: #cccccc;"> <th colspan="4" style="text-align: left; padding: 5px;">Description</th> <th style="text-align: left; padding: 5px;">Tolerance</th> <th style="text-align: left; padding: 5px;">Test Methods</th> </tr> </thead> <tbody> <tr> <td style="padding: 5px;">Coating</td> <td colspan="5" style="padding: 5px;">Coated with an grey high-temperature treatment</td> </tr> <tr> <td style="padding: 5px;">Weight</td> <td></td> <td style="padding: 5px;">1.275</td> <td style="padding: 5px;">g/cm2</td> <td style="padding: 5px;">+/- 10%</td> <td style="padding: 5px;">DIN EN 12127</td> </tr> <tr> <td style="padding: 5px;">Thickness</td> <td></td> <td style="padding: 5px;">1,60</td> <td style="padding: 5px;">mm</td> <td style="padding: 5px;">+/- 10%</td> <td style="padding: 5px;">DIN EN ISO 5084</td> </tr> <tr> <td style="padding: 5px;">Tensile Strength</td> <td style="padding: 5px;">Warp Weft</td> <td style="padding: 5px;">> 5.500 >2.500</td> <td style="padding: 5px;">N/5cm N/5cm</td> <td></td> <td></td> </tr> <tr> <td style="padding: 5px;">Temperature Resistance</td> <td colspan="5" style="padding: 5px;">700°C</td> </tr> </tbody> </table>					Description				Tolerance	Test Methods	Coating	Coated with an grey high-temperature treatment					Weight		1.275	g/cm2	+/- 10%	DIN EN 12127	Thickness		1,60	mm	+/- 10%	DIN EN ISO 5084	Tensile Strength	Warp Weft	> 5.500 >2.500	N/5cm N/5cm			Temperature Resistance	700°C				
Description				Tolerance	Test Methods																																				
Coating	Coated with an grey high-temperature treatment																																								
Weight		1.275	g/cm2	+/- 10%	DIN EN 12127																																				
Thickness		1,60	mm	+/- 10%	DIN EN ISO 5084																																				
Tensile Strength	Warp Weft	> 5.500 >2.500	N/5cm N/5cm																																						
Temperature Resistance	700°C																																								

NB: Unless otherwise stated, all values quoted are nominal measurements. The information contained in this data sheet is believed to be true at the time of printing. Any statements contained or inferred to within are an expression of opinion and presented without guarantee. It is up to the user to determine suitability of use, or potential patent infringement for specific applications.