



DESCRIPTION

Isofrax 1260°C Paper products are manufactured from Isofrax alkaline earth silicate wool, blended with specially selected organic binders to give flexible papers with exceptional characteristics.

Advanced production techniques ensure a highly uniform structure enhanced by low thermal conductivity, good handling strength and a smooth surface. Isofrax 1260°C Papers are available in a range of thicknesses and roll sizes.

GENERAL CHARACTERISTICS

Isofrax 1260°C Paper has the following outstanding characteristics:

- High temperature stability
- Good handling strength
- Lightweight
- Excellent flexibility
- Easy to wrap, cut and shape

TYPICAL APPLICATIONS

- High temperature gaskets and seals
- Ingot mould liners
- Automotive heat shields
- Molten metal transfer systems (back-up insulation)
- Insulating wrap for shrouds/stopper rods in steel manufacture

Any new and/or special use of these products, whether or not in an application listed in our literature, must be submitted to our technical department for their prior written approval.

*Start saving energy now.
Contact your local distributor.*

Unifrax Ltd.

T:+44 (0)1744 88 7600

F:+44 (0)1744 88 9916

www.unifrax.com

TYPICAL PRODUCT PARAMETERS

Isofrax 1260°C Paper	
Typical Chemical Analysis (fibre wt. %)	
SiO ₂	70.0 - 80.0
MgO	>18.0 - 27.0
Trace	<4.0
Physical Properties	
Colour	White
Melting Point (°C)	>1500
Product Density (kg/m ³)	140 - 160
Tensile Strength (kPa)	350
Mean Fibre Diameter (microns)	4.0
Loss on Ignition (wt.%)	<10.0
Thermal Conductivity (W/mK)	
Mean Temp.	
400 °C	0.08
600 °C	0.11
800 °C	0.16
1000 °C	0.21

Isofrax products are suitable for a variety of high temperature applications. For specific advice on application and operational temperature limits please contact your nearest Unifrax Engineering office. Where appropriate Physical Properties data measured according to EN 1094-1.

AVAILABILITY

Thickness (mm)	Isofrax 1260°C Paper	Roll Length (m)		
		Roll Width (mm)	610	1000
1	✓	125	330	330
2	✓	60	180	180
3	✓	35	110	110
4	✓	25	80	80
5	✓	20	60	60
6	✓	15	45	45

Other thicknesses / sizes may be available on request subject to minimum order requirements.

HANDLING INFORMATION

A Material Safety Data Sheet has been issued describing the health, safety and environmental properties of this product, identifying the potential hazards and giving advice on handling precautions and emergency procedures. This must be consulted and fully understood before handling, storage or use.

Supplied by:

Information contained in this publication is for illustrative purposes only and is not intended to create any contractual obligation. Further information and advice on specific details of the products described should be obtained in writing from a Unifrax Corporation company (Unifrax España, Unifrax France, Unifrax GmbH, Unifrax Italia, Unifrax Limited, Unifrax s.r.o.). Unifrax maintains a continuous programme of product development and reserves the right to change product specifications without prior notice. Therefore, it maintains at all times the responsibility of the customer to ensure that Unifrax materials are suitable for the particular purpose intended. Similarly, insofar as materials not manufactured nor supplied by Unifrax are used in conjunction with or instead of Unifrax materials, the customer should ensure that all technical data and other information relating to such materials has been obtained from the manufacturer or supplier. Unifrax accepts no liability arising from the use of such materials. All sales made by a Unifrax Corporation company are subject to that company's Terms and Conditions of Sale, copies of which are available on request.